

Product specification	Applied standard	Value 4 mm / 2.5 mm
Usage classification	EN 685 / EN ISO 10874	33
Conforms to the European standard	EN 14041	CE
Wear layer (mm)	-	0.55
Thermal conductivity, $\lambda$ (W/m.K)	EN 12667	0.097
Reaction to fire	EN 13501 - 1	Bfl s1
Slip resistance (-)	DIN 51130 & AS/NZS 4856 EN 14041 & EN 13893	R9 DS
Colour fastness (-)	EN 20105 B02	$\geq 6$
Dimensional stability (%)	EN 434	0.10 / 0.15
Scratch resistance	EN 660-2	Class T
Hygrothermal Properties for use with floor heating	EN 12524	Up to 27°C
Toxicity	EN 71	No heavy metals
Volatile organic compounds (French VOC emission)	ISO 16000-3/-6/-9/-11	A+
Formaldehyde emission (Class)	EN 717-1	E1
AgBB classification after 28 days - TVOC without NIK (mg/m <sup>3</sup> )	DIBt & AgBB	$\geq 0.1$
Suitability for use with castor chairs (-)	EN 425	2500
Resistance to chemicals (-)	EN 423 / EN ISO 26987	0 / alcohol 2
Residual indentation	EN 433	$\geq 0.1$ mm
Curling	EN 434 / EN ISO 23999	$\geq 2$ mm
Guarantee	-	20 years residential use 5 years commercial use / 10 years commercial use